

REF. GDFT002

ISO 9001 CERTIFIED

Novamid® B33 is a Polyamide 6 resin produced by the CPL reaction in a polymerization process. The polymer is especially suitable for extrusion applications in general like high tenacity yarns, corrugated tubes, film extrusion, and certain compounding applications.

Product Specifications	Values	Standard method
Relative viscosity	3,31 +/- 0,1	ISO 1628
Monomer % max.	≤ 0,60	ISO 599
Moisture content % max.	≤ 0,1	NAPPA-032

Main properties	Unit	Value	Testing method
Melting point	°C	220	ISO 3146
Density	g/cm ³	1,16	ISO 1183
Apparent density	g/cm ³	0,69	NAPPA-059
Chip size (length-diameter)	mm	2,5	NAPPA-045

Packaging	Big bag / Octabin / Silo truck
-----------	--------------------------------

Disclaimer: All the information submitted is based on our knowledge and experience. The shown values have been established by using standardized tests performed at our plant. Figures should be regarded as guidance and not as a minimum values. The affectation of the process and applications by different factors or conditions cannot be guaranteed, therefore, users are recommended to perform the test in order to determine the suitability of the product for one particular use.

Central offices

Independencia, 21. 3ª
50001 Zaragoza. Spain
T +34 976 216 129
F +34 976 238 703
www.novamid.com

Plant

Poligono de Malpica, Ctra de Barcelona
50016 Zaragoza. Spain
T +34 976 465 579
F +34 976 574 108

NOVAMID®
Registered trade mark by NUREL ENGINEERING POLYMERS